

Vydyne® 21SPC

polyamide 66

Vydyne 21SPC is a general-purpose PA66 resin. Available in natural color. It is designed principally for injection-molding fabrication. This resin offers a well balanced combination of engineering properties characterized by high strength; rigidity; good toughness; high melt point; good surface lubricity; abrasion resistance; and resistance to many chemicals, machine and motor oils, solvents and gasoline.

Vydyne 21SPC permits production of molded parts with good initial color plus good property and color retention when using regrind. This resin is recognized by Underwriters Laboratories and conforms to the requirements of many industrial, federal and military specifications for premium-quality, general-purpose PA66 resins.

Internally and externally lubricated for improved machine feed and exceptional mold release. Vydyne 21SPC is intended for use in

high-productivity applications. In many applications, the molding cycle can be reduced because parts may be removed from the cavity at higher temperatures. In difficult molds where parts have a tendency to stick in the cavity, Vydyne 21SPC can reduce or eliminate the need for mold release sprays. Critical molded-part dimensions should be checked against specifications before implementing shorter molding cycles on a routine production basis.

Typical Applications/End Uses:

Vydyne 21SPC has been used in many molding applications such as terminal blocks, bearings, bushings, cams, electrical connectors and housings, electrical cable ties/tie straps and many other hardware and general industrial parts.

General			
Material Status	• Commercial: Active		
Availability	• Asia Pacific	• Europe	• North America
Additive	• Lubricant		
Features	• Abrasion Resistant • Chemical Resistant • Fast Molding Cycle • Gasoline Resistant	• General Purpose • Good Mold Release • Good Toughness • High Rigidity	• High Strength • Lubricated • Oil Resistant • Solvent Resistant
Uses	• Bearings • Bushings • Cams	• Connectors • Electrical/Electronic Applications • Fasteners	• General Purpose • Housings • Industrial Applications
Agency Ratings	• ASTM D4066 PA0111 • ASTM D6779 PA0111 • EC1935/2004	• EU 10/2011 • EU 2023/2006 • FDA 21 CFR 177.1500	• FED L-P-410A • MIL M-20693B • NSF STD-51
RoHS Compliance	• RoHS Compliant		
Automotive Specifications	• FORD WSK-M4D647-A	• GM GMP.PA66.005	• GM QK 002921
UL File Number	• E70062		
Appearance	• Natural Color		
Forms	• Pellets		
Processing Method	• Injection Molding		

Vydyne® 21SPC
polyamide 66

Physical	Dry	Conditioned	Unit	TestMethod
Density	1.14	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow : 23°C, 2.00 mm	1.7	--	%	
Flow : 23°C, 2.00 mm	1.8	--	%	
Water Absorption				ISO 62
24 hr, 23°C	1.2	--	%	
Equilibrium, 23°C, 50% RH	2.4	--	%	
Outdoor Suitability (All Colors)	f2	--		UL 746C
Mechanical	Dry	Conditioned	Unit	TestMethod
Tensile Modulus (23°C)	3100	1400	MPa	ISO 527-2
Tensile Stress				ISO 527-2
Yield, 23°C	82.0	55.0	MPa	
Break, 23°C	55.0	45.0	MPa	
Tensile Strain (Yield, 23°C)	5.0	25	%	ISO 527-2
Nominal Tensile Strain at Break (23°C)	25	>50	%	ISO 527-2
Flexural Modulus (23°C)	2900	1500	MPa	ISO 178
Flexural Strength (23°C)	80.0	50.0	MPa	ISO 178
Poisson's Ratio	0.40	--		ISO 527
Impact	Dry	Conditioned	Unit	TestMethod
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	5.0	7.0	kJ/m ²	
23°C	6.0	20	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	No Break	No Break		
23°C	No Break	No Break		
Notched Izod Impact Strength				ISO 180
-30°C	5.0	7.0	kJ/m ²	
23°C	6.0	20	kJ/m ²	

Vydyne® 21SPC
polyamide 66

Thermal	Dry	Conditioned	Unit	TestMethod
Heat Deflection Temperature				ISO 75-2/B
0.45 MPa, Unannealed	200	--	°C	ISO 75-2/A
1.8 MPa, Unannealed	70.0	--	°C	ISO 11357-3
Melting Temperature	260	--	°C	ISO 11359-2
CLTE				
Flow : 23 to 55°C	1.0E-4	--	cm/cm/°C	
Transverse : 23 to 55°C	1.0E-4	--	cm/cm/°C	
RTI Elec				UL 746
0.40 mm	130	--	°C	
0.71 mm	130	--	°C	
1.5 mm	130	--	°C	
3.0 mm	130	--	°C	
RTI Imp				UL 746
0.40 mm	75.0	--	°C	
0.71 mm	75.0	--	°C	
1.5 mm	75.0	--	°C	
3.0 mm	75.0	--	°C	
RTI Str				UL 746
0.40 mm	75.0	--	°C	
0.71 mm	85.0	--	°C	
1.5 mm	85.0	--	°C	
3.0 mm	85.0	--	°C	
Electrical	Dry	Conditioned	Unit	TestMethod
Volume Resistivity (0.750 mm)	1.0E+13	--	ohms-cm	IEC 60093
Dielectric Strength (1.00 mm)	26	--	kV/mm	IEC 60243
Arc Resistance (3.00 mm)	PLC5	--		ASTM D495
Comparative Tracking Index (3.00 mm)	600	--	V	IEC 60112
High Amp Arc Ignition (HAI)				UL 746
0.40 mm	PLC1	--		
0.71 mm	PLC0	--		
1.5 mm	PLC0	--		
3.0 mm	PLC0	--		
High Voltage Arc Tracking Rate (HVTR)	PLC0	--		UL 746
Hot-wire Ignition (HWI)				UL 746
0.40 mm	PLC4	--		
0.71 mm	PLC4	--		
1.5 mm	PLC3	--		
3.0 mm	PLC2	--		

Vydyne® 21SPC

polyamide 66

Flammability	Dry	Conditioned	Unit	TestMethod
Flame Rating				UL94
0.40 mm	V-2	--		
0.71 mm	V-2	--		
1.5 mm	V-2	--		
3.0 mm	V-2	--		
Glow Wire Flammability Index				IEC 60695-2-12
0.40 mm	960	--	°C	
0.71 mm	960	--	°C	
1.5 mm	960	--	°C	
3.0 mm	960	--	°C	
Glow Wire Ignition Temperature				IEC 60695-2-13
0.40 mm	825	--	°C	
0.71 mm	850	--	°C	
1.5 mm	850	--	°C	
3.0 mm	850	--	°C	
Oxygen Index	25	--	%	ISO 4589-2
Injection		Dry Unit		
Drying Temperature		< 70 °C		
Drying Time		1.0 to 3.0 hr		
Suggested Max Regrind		50%		
Rear Temperature		260 to 280 °C		
Middle Temperature		270 to 285 °C		
Front Temperature		280 to 290 °C		
Nozzle Temperature		280 to 300 °C		
Processing (Melt) Temp		285 to 300 °C		
Mold Temperature		65 to 95 °C		

Notes

Typical properties: these are not to be construed as specifications.

¹ Typical properties: these are not to be construed as specifications.



North America

+1 888 927 2363

Europe

+32 10 608 600

Asia

+86 21 6340 3300

Disclaimer of Warranty and Liability

NOTICE: Although the information and recommendations set forth herein (hereinafter "information") are presented in good faith and believed to be correct as of the date hereof, Ascend Performance Materials Operations makes no representations or warranties as to the completeness or accuracy thereof.

Information is supplied upon the condition that the persons receiving same will make their own determination as to its suitability for their purposes prior to use. In no event will Ascend Performance Materials Operations be responsible for damages of any nature whatsoever resulting from the use of or reliance upon information or the products to which information refers. Nothing contained herein is to be construed as a recommendation to use any product, equipment or formulation in conflict with any patent, and Ascend Performance Materials Operations makes no representation or warranty, express or implied, that use thereof will not infringe any patent. No representations or warranties, either express or implied, of merchantability, fitness for a particular purpose or of any other nature are made hereunder with respect to information or the product to which information refers.