

Zytel® MT409AHS BK010

Zytel® MT409AHS BK010 is a Medium Toughened, high performance, heat stabilized, black polyamide 66 resin having good stiffness and improved knit line strength with superior toughness and processability.

Property	Test Method	Units	Value	
			DAM	50%RH
Identification				
Resin Identification	ISO 1043		PA66-I	
Part Marking Code	ISO 11469		>PA66-I<	
Mechanical				
Yield Stress	ISO 527	MPa (kpsi)	60 (8.7)	42 (6.1)
Yield Strain	ISO 527	%	6	27
Nominal Strain at Break	ISO 527	%	29	>50
Tensile Modulus	ISO 527	MPa (kpsi)	2400 (348)	1075 (156)
Tensile Stress	ISO 527	MPa (kpsi)		
@ 50% Strain			61 (8.8)	43 (6.2)
Flexural Modulus	ISO 178	MPa (kpsi)	2200 (319)	1075 (156)
Notched Charpy Impact Strength	ISO 179/1eA	kJ/m2		
-40°C (-40°F)			12	
23°C (73°F)			19	

Contact DuPont for Material Safety Data Sheet, general guides and/or additional information about ventilation, handling, purging, drying, etc.
 ISO Mechanical properties measured at 4.0mm, ISO Electrical properties measured at 2.0mm, and all ASTM properties measured at 3.2mm.
 Test temperatures are 23°C unless otherwise stated.

The DuPont Oval Logo, DuPont™, The miracles of science™ and Zytel® are trademarks or registered trademarks of DuPont Company. Copyright© 2007.

070627/070627

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials, additives or pigments or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since DuPont cannot anticipate all variations in actual end-use conditions DuPont makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights. DuPont advises you to seek independent counsel for a freedom to practice opinion on the intended application or end-use of our products. CAUTION: Do not use DuPont materials in medical application involving implantation in the human body or contact with internal body fluids or tissues unless the material has been provided from DuPont under a written contract that is consistent with DuPont policy regarding medical applications and expressly acknowledges the contemplated use. For further information, please contact your DuPont representative. You may also request a copy of DuPont POLICY Regarding Medical Applications H-50103-2 and DuPont CAUTION Regarding Medical Applications ... H-50102-2.

Zytel® MT409AHS BK010

Property	Test Method	Units	Value	
			DAM	50%RH
Thermal				
Deflection Temperature	ISO 75-1/-2	°C (°F)		
0.45MPa			187 (369)	
1.80MPa			65 (149)	
Melting Temperature	ISO 11357-1/-3	°C (°F)		
10°C/min			262 (504)	
CLTE, Parallel	ISO 11359-1/-2	E-4/C (E-4/F)		
-40 - 23°C (-40 - 73°F)			0.9 (0.5)	
-30 - 30°C (-22 - 86°F)			0.9 (0.5)	
23 - 55°C (73 - 130°F)			1.0 (0.6)	
55 - 160°C (130 - 320°F)			1.2 (0.7)	
CLTE, Normal	ISO 11359-1/-2	E-4/C (E-4/F)		
-40 - 23°C (-40 - 73°F)			1.0 (0.6)	
-30 - 30°C (-22 - 86°F)			1.0 (0.6)	
23 - 55°C (73 - 130°F)			1.0 (0.6)	
55 - 160°C (130 - 320°F)			1.4 (0.8)	
Electrical				
Surface Resistivity	IEC 60093	ohm	3.0E15	4.7E11
Volume Resistivity	IEC 60093	ohm m	2.0E13	9.7E9
Electric Strength	IEC 60243-1	kV/mm (V/mil)	25 (635)	22 (560)
Relative Permittivity	IEC 60250			
1E2 Hz			3.9	9.
1E6 Hz			3.7	8
Dissipation Factor	IEC 60250	E-4		
1E2 Hz			60	4.
1E6 Hz			130	0
CTI	IEC 60112	V	525	510
CTI	UL 746A	V	600	0

Contact DuPont for Material Safety Data Sheet, general guides and/or additional information about ventilation, handling, purging, drying, etc.
 ISO Mechanical properties measured at 4.0mm, ISO Electrical properties measured at 2.0mm, and all ASTM properties measured at 3.2mm.
 Test temperatures are 23°C unless otherwise stated.

The DuPont Oval Logo, DuPont™, The miracles of science™ and Zytel® are trademarks or registered trademarks of DuPont Company. Copyright© 2007.

070627/070627

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials, additives or pigments or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since DuPont cannot anticipate all variations in actual end-use conditions DuPont makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights. DuPont advises you to seek independent counsel for a freedom to practice opinion on the intended application or end-use of our products. CAUTION: Do not use DuPont materials in medical application involving implantation in the human body or contact with internal body fluids or tissues unless the material has been provided from DuPont under a written contract that is consistent with DuPont policy regarding medical applications and expressly acknowledges the contemplated use. For further information, please contact your DuPont representative. You may also request a copy of DuPont POLICY Regarding Medical Applications H-50103-2 and DuPont CAUTION Regarding Medical Applications ... H-50102-2.

Zytel® MT409AHS BK010

Property	Test Method	Units	Value	
			DAM	50%RH
Flammability				
Flammability Classification 0.8mm	IEC 60695-11-10		HB	
Flammability Classification 0.8mm	UL94		HB	
High Amperage Arc Ignition Resistance 0.8mm	UL 746A	arcs	120	
1.5mm			120	
3.0mm			120	
Hot Wire Ignition 0.8mm	UL 746A	s	7	
1.5mm			7	
3.0mm			7	
Temperature Index				
RTI, Electrical 0.8mm	UL 746B	°C	130	
RTI, Impact 0.8mm	UL 746B	°C	65	
1.5mm			105	
RTI, Strength 0.8mm	UL 746B	°C	95	
1.5mm			105	
3.0mm			110	
Other				
Density	ISO 1183	kg/m3 (g/cm3)	1110 (1.11)	
Water Absorption Immersion 24h	ISO 62, Similar to	%	0.9	
Molding Shrinkage Normal, 2.0mm	ISO 294-4	%	1.7	
Parallel, 2.0mm			1.7	

Contact DuPont for Material Safety Data Sheet, general guides and/or additional information about ventilation, handling, purging, drying, etc.
 ISO Mechanical properties measured at 4.0mm, ISO Electrical properties measured at 2.0mm, and all ASTM properties measured at 3.2mm.
 Test temperatures are 23°C unless otherwise stated.

The DuPont Oval Logo, DuPont™, The miracles of science™ and Zytel® are trademarks or registered trademarks of DuPont Company. Copyright© 2007.

070627/070627

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials, additives or pigments or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since DuPont cannot anticipate all variations in actual end-use conditions DuPont makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights. DuPont advises you to seek independent counsel for a freedom to practice opinion on the intended application or end-use of our products. CAUTION: Do not use DuPont materials in medical application involving implantation in the human body or contact with internal body fluids or tissues unless the material has been provided from DuPont under a written contract that is consistent with DuPont policy regarding medical applications and expressly acknowledges the contemplated use. For further information, please contact your DuPont representative. You may also request a copy of DuPont POLICY Regarding Medical Applications H-50103-2 and DuPont CAUTION Regarding Medical Applications ... H-50102-2.

Zytel® MT409AHS BK010

Property	Test Method	Units	Value	
			DAM	50%RH
Processing				
Melt Temperature Range		°C (°F)	270-300 (520-570)	
Melt Temperature Optimum		°C (°F)	280 (535)	
Mold Temperature Range		°C (°F)	50-90 (120-190)	
Mold Temperature Optimum		°C (°F)	70 (160)	
Drying Time, Dehumidified Dryer		h	2-4	
Drying Temperature		°C (°F)	80 (175)	
Processing Moisture Content		%	<0.20	

Contact DuPont for Material Safety Data Sheet, general guides and/or additional information about ventilation, handling, purging, drying, etc.
 ISO Mechanical properties measured at 4.0mm, ISO Electrical properties measured at 2.0mm, and all ASTM properties measured at 3.2mm.
 Test temperatures are 23°C unless otherwise stated.

The DuPont Oval Logo, DuPont™, The miracles of science™ and Zytel® are trademarks or registered trademarks of DuPont Company. Copyright© 2007.

070627/070627

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials, additives or pigments or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since DuPont cannot anticipate all variations in actual end-use conditions DuPont makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights. DuPont advises you to seek independent counsel for a freedom to practice opinion on the intended application or end-use of our products. CAUTION: Do not use DuPont materials in medical application involving implantation in the human body or contact with internal body fluids or tissues unless the material has been provided from DuPont under a written contract that is consistent with DuPont policy regarding medical applications and expressly acknowledges the contemplated use. For further information, please contact your DuPont representative. You may also request a copy of DuPont POLICY Regarding Medical Applications H-50103-2 and DuPont CAUTION Regarding Medical Applications ... H-50102-2.